

HARDENER H2

INSTRUCTIONS FOR USE

Hardener H2 is specially formulated for use with Newclay, Claydium and NovaClay air-drying modelling clays. Hardener H2 imparts an all-through additional hardness to your models. For surface, or case-hardening, your model or you wish your piece to stay workable for an extended time, use Hardener H1. Hardeners H1 and H2 are NOT interchangeable.

Use Hardener H2 at up to 5% by weight in the clay (e.g. 50g H2 to 1kg clay). Knead the Hardener H2 into the required amount of clay just prior to use. Clay treated in this way should be consumed that day.

When the piece is dry a considerable increase in hardness (compared to untreated clay) can be expected. The degree of hardness can be increased further by slowly heating the piece up to a maximum of 200°C.

Unused Hardener H2 should be stored in an air-tight container in a dry place.

NOTE: *Although non-toxic and completely safe to use, Hardener H2 powder is an eye irritant, and young children must be supervised at all times. In the unlikely event of Hardener H2 finding its way into the eyes of the user, irrigate the eyes with plenty of water.*